

Fire Test Certificate – Specimen

Fabric: The West End Collection - Palladium
Type: NFPA 701

J&C Joel 
Inspiration in every performance



(28115) 21, Yangcheong-3gil, Ochang-eup, cheongwon-gu, Cheongju-si Chungbuk, Kor
Tel : 043-711-8875 Fax : 043-711-88

TEST REPORT



REPORT NO. : M270-20-14023
SAMPLE RECEIVED DATE : 2020-09-14
TEST STARTED DATE : 2020-09-14
REPORT ISSUED DATE : 2020-09-22
PAGE : 1 OF 2

DESCRIPTION : ONE(1) PIECE OF SUBMITTED CUTTING SAID TO BE FABRIC.

=====

ITEM : PALLADIUM

=====

TEST CONDUCTED : AS REQUESTED BY THE APPLICANT, FOR DETAILS PLEASE SEE ATTACHED PAGE

=====

PREPARED AND CHECKED BY
FOR FITI



HONG-KWAN KIM
QUALITY MANAGER

AUTHORIZED BY
FOR FITI



JE-GOO JUN
PRESIDENT

※ Report Verification No.: GFZ7-IEH5-HQLL ※

(You can see the authenticity of your test report through the above "Report Verification No." at FITI homepage.)

e-DOCUMENT SERVICE

The test results contained in this report are limited to results on the sample(s) that is provided by client and are not necessarily indicative or representative of the qualities of the lot from which the sample(s) was taken or of all products. Results contained in this report are not based on the quality certification

Fire Test Certificate – Specimen

Fabric: The West End Collection - Palladium
Type: NFPA 701

J&C Joel
Inspiration in every performance



(28115) 21, Yangcheong-3gil, Ochang-eup, cheongwon-gu, Cheongju-si Chungbuk, K
Tel : 043-711-8875 Fax : 043-711-4

REPORT NO.: M270-20-14023
PAGE : 2 OF 2

01. FLAMMABILITY (NFPA 701 : 2019, METHOD 1)

#1					
SAMPLE NO.	WEIGHT(g)		WEIGHT LOSS(%)	AFTER FLAME TIME(s)	DRIP BURN(s)
	ORIGINAL	AFTER TEST			
1	17.5	13.6	23.2	0	0
2	17.5	12.7	27.5	0	0
3	17.7	12.9	27.1	0	0
4	17.7	13.9	21.6	0	0
5	17.6	13.1	25.6	0	0
6	17.4	12.2	29.9	0	0
7	17.5	13.3	24.0	0	0
8	17.6	13.5	23.3	0	0
9	17.5	13.7	21.7	0	0
10	17.6	13.0	26.1	0	0
AVG.	17.6	13.2	25.0	0	0
CONCLUSION	BASED UPON THE RESULTS, THE SUBMITTED SAMPLE MEETS PERFORMANCE REQUIREMENTS AS STATED IN NFPA 701 TEST METHOD 1(2019).				

NOTE) • REQUIREMENT

DRIP BURN(s)	WEIGHT LOSS(%)	NO INDIVIDUAL SPECIMEN'S WEIGHT LOSS EXCEED THE MEAN VALUE PLUS 3 STANDARD. STANDARD DEVIATION = 2.70 THE MEAN VALUE PLUS 3 STANDARD = 33.1
AVG. : LESS THAN 2	AVG. : LESS THAN 40	

- TESTS WERE CONDUCTED ONLY IN THE ORIGINAL STATE BY THE CLIENT'S REQUEST.

** End of The Report **

SAMPLE :

e-DOCUMENT SERVICE

The test results contained in this report are limited to results on the sample(s) that is provided by client and are not necessarily indicative or representative