Sateen Lining

Perfect For: Masking • Decorative/Scenic • Film & TV • Stage • Lining

J&C Joel

the inspiration behind the performance

Contents

J&C Joel
the inspiration behind the performance

Composition & Care

137 cm 3

Fire Certificate

BS5867 Part 2 Type B 4

TECHNICAL

NDFR
Non Durably Flame Retardant
chemically treated with a water solution and if wetted in any way should be retreated

DFR
Durably Flame Retardant
chemically treated to withstand a number of cleanings

IFR
Inherently Flame Retardant
woven from fibres with a high flame retardancy

FR
Flame Retardant
chemically treated to an individual specification

NOT FR
Not Flame Retardant no flame retardant treatment

Confirmation that the fabric meets one or more flame retardant standards

BS5867 BS5867 Pt2 B is the British Standard for flame retardant fabrics used for curtains and drapes

BS5852 BS5852 Pt1 is the British Standard for flammability of upholstered composites for seating

BS4790 BS4790: 1987 Determination of the effects of a small source of ignition on textile floor coverings hot metal nut method (method 1, loose laid)

EN13773: 2003 Meets European fire safety standards for vertically hung fabrics. Burning behavior, ignitability testing of curtain fabric for use in the contract market.

TL 1080-0002/8 German Military Specification for horizontally tested materials

EN14041 Details the requirement for CE Marking of textiles, laminate and resilient floor coverings

BS7905-1:2001 Lifting equipment for performance, broadcast and similar applications.

ATTRIBUTES

Approx roll length of material in linear metres (m) & feet (ft)

Approx width of material in centimetres (cm) & inches (")

Approx weight in grams per metre squared (g/m^2)

Approx thickness in (mm)

M1, M2, M4 Conforms to French Fire Regulations

B1, B2 Conforms to German Fire Regulations DIN 4102

IMO Conforms to International Maritime Organisation regulations

Classe Uno Meets Italian Fire Regulations

BS EN13501-1 Fire Classification of construction, products and building elements. Classification using test data from reaction to fire tests

CFC EN ISO 9239-1 Reaction to fire test. Horizontal surface spread of flame on floor covering system. Determination of the burning behaviour using a retardant heat source

NFPA 701 NFPA 701: (USA) Standard Methods of Fire Tests for Flame Propagation of Textiles and Films

EN9239-1 Reaction to fire tests – horizontal surface spread of flame on floor covering systems

DIN EN1021 Meets European fire safety standards for exposure to different ignition sources, namely a lit cigarette and butane flame. Assessment of the ignitability of upholstered furniture

Datasheet - Fabrics & Flooring

Sateen Lining

J&C Joel

the inspiration behind the performance

To ensure you get the best from the product supplied to you, we advise you follow the care instructions within this datasheet.

Fabric	**Flame Retardancy**	NDFR
	Fire Certification	BS5867
	Brand Name (and Manufacturer)	J&C Joel Ltd.
	Material (Blending Ratio)	100% Cotton
	Construction of Fabric	Plain Weave
Chemicals	**Surface Treatments**	Dyed & Flameproofed
	Brand Name of Flame Retardant Chemicals	Organo Phosphate Compound
	Chemical name of Flame Retardant Chemicals	N/A
	Process of Flame Retardant Chemicals	N/A
Care	**Information**	Non-Durably Flame Retardant. This means that the fabric is chemically treated and if wet (in any way) should be retreated to meet the flammability requirements of BS5867 Part 2 Type B. Therefore, the cloth will not withstand wet cleaning and should be re-flame proofed whenever wet. The cloth can be professionally dry cleaned using the correct chemical process. Notwithstanding the aforementioned, it would be our advice to only dry clean this material periodically. We would suggest that the curtain be soft-brushed on a regular basis and periodically cleaned using a vacuum and drapery attachment. Commercial flame retardants may alter the aesthetics, appearance, colour or performance of the textile material. This fabric is not pre-shrunk.
	Laundering Treatment	 Dry Clean Only · Do Not Wash · Do Not Bleach · Do Not Iron · Do Not Tumble Dry
Notes		

Fire Rating:
NDFR

Approx Roll Length:
80m / 262ft

Width:
137cm / 54”

Weight:
150 g/m^2

Fire Certification:
BS5867

Colours Available

For further information please contact our sales team **sales@jcjoel.com**

Fire Test Certificate

Fabric: Sateen Lining
Type: BS5867 Part 2 Type B

J&C Joel
the inspiration behind the performance

Wira House, West Park Ring Road,
Leeds, LS16 6QL, UK.
Telephone: +44 (0)113 259 1999
Email: info@bttg.co.uk
Website: www.bttg.co.uk

Date: 01 August 2017

Our Ref: **53519-34**
Your Ref: -

Client:	J. & C. Joel Limited Corporation Mill Corporation Street Sowerby Bridge Halifax HX6 2QQ
Job Title:	Surface Ignition Of Curtains & Drapes (Type B)
Client's Order No:	-
Date of Receipt: Date of Test Start:	19 May 2017 08 June 2017
Description of Sample(s):	One sample identified as follows was received for testing: Sateen Lining, stated to be NDFR
Work Requested:	We were asked to make the following test: BS 5867: Part 2: 2008 (2015): Type B Curtains, Drapes and Blinds

1066

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.
A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.
The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.
Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2017 Shirley Technologies Limited. All rights reserved.

BTTG
TESTING • CERTIFICATION • AUDITING

Wira House, West Park Ring Road,
Leeds, LS16 6QL, UK.
Telephone: +44 (0)113 259 1999
Email: info@bttg.co.uk
Website: www.bttg.co.uk

Date: 01 August 2017

Our Ref: **53519-34**
Your Ref: -

J. & C. Joel Limited

Sample was identified as follows:

Sateen Lining, stated to be NDFR

BS 5867: Part 2: 2008 (2015): Type B Curtains, Drapes and Blinds

Pre-Treatment
No water treatment required as the sample was stated to be non durable flame retardant.

Conditioning
The test specimens were conditioned for at least 24 hours in the standard atmosphere of 60 ± 5 % relative humidity (R.H.) and 20 ± 2 °C.

Testing
Three specimens from both length and width were tested in accordance with BS EN ISO 15025: Procedure A (surface ignition):2002. The sample was tested at 20°C and 60% relative humidity (R.H.).

Each specimen was subjected to an applied flame using propane and a 15 second flame application time. The results obtained (shown in the table below) were assessed according to the requirements of BS 5867: Part 2:2008 (2015).

Test results relate only to the sample tested.

The results for all tests are given in the table(s) on the following page(s).

Reported by:.....
J Coleman
Fire Technician

Countersigned By:.....
P Doherty
Operational Head

Enquiries concerning this report should be addressed to Customer Services.

ilac-MRA UKAS TESTING 1066

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.
A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.
The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.
Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2017 Shirley Technologies Limited. All rights reserved.

Wira House, West Park Ring Road,
Leeds, LS16 6QL, UK.
Telephone: +44 (0)113 259 1999
Email: info@bttg.co.uk
Website: www.bttg.co.uk

Date: 01 August 2017

Our Ref: **53519-34**
Your Ref: -

TESTING • CERTIFICATION • AUDITING

J. & C. Joel Limited

RESULTS

Sample Ref: Sateen Lining, stated to be NDFR

BS 5867: Part 2: 2008 (2015): Type B Curtains, Drapes and Blinds
Testing as received.

	Length			Width		
Specimen No.	**1**	**2**	**3**	**4**	**5**	**6**
Flame reached an edge	No	No	No	No	No	No
Hole reached an edge	No	No	No	No	No	No
Flaming debris separated	No	No	No	No	No	No

Requirements
Any "Yes" means fail except if only one specimen fails a further 6 specimens are tested, it the second 6 specimens all pass the result is a pass.

Result: Pass

Conclusion
The fabric meets the Type B performance requirements of BS 5867: Part 2: 2008 – the fabric must be clearly labelled `If wetted in any way it is essential to re-treat the fabric to meet flammability requirements`.

The material should be identified with the manufacturers name, trademark or other identifying mark, the statement `Flammability complies with the requirements of BS 5867: Part 2, Type B and instructions of any special precautions to be taken concerning care (including cleansing) of the curtain, drape or window blind to be manufactured from the fabric, preferably using an appropriate care labelling symbol in accordance with BS EN 23758 and taking account of the pre-treatment used in this test and the requirements of Clause 4 of BS 5867: Part 2: 2008 (2011). If the fabric is unsuitable for cleansing, this shall be stated.

Uncertainty Budget
There is no uncertainty budget associated with BS 5867: Part 2: Type B as no measurements are determined, the pass/fail criteria is assessed visually.

ilac-MRA UKAS TESTING
1066

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL.
A company registered in England & Wales with company number 04669651. VAT Number GB 816764800.
The supply of all goods and services is subject to our standard terms of business, copies of which are available on request.
Our laboratories are accredited to EN ISO/IEC 17025.

Copyright © 2017 Shirley Technologies Limited. All rights reserved.

J&C Joel

the inspiration behind the performance

UK
J&C Joel United Kingdom - HQ
uksales@jcjoel.com

EU
J&C Joel Europe
eusales@jcjoel.com

ME
J&C Joel Middle East
uaesales@jcjoel.com

VN
J&C Joel Vietnam
asiasales@jcjoel.com

MO
J&C Joel Macau
asiasales@jcjoel.com

HK
J&C Joel Hong Kong
asiasales@jcjoel.com